

Patent- og  
Varemærkestyrelsen  
Erhvervsministeriet

File 351:Derwent WPI 1963-2001/UD,UM &JP=200147  
(c) 2001 Derwent Info Ltd

DIALOG(R)File 351:Derwent WPI  
(c) 2001 Derwent Info Ltd. All rts. reserv.

004180710

WPI Acc No: 1985-007590/198502

KRAM Acc No: C85-003090

KRPX Acc No: N85-005282

Structure for heat-insulation of flat roofs - comprises closed cell foamed plastic layer and top-layer of filled organic binder

Patent Assignee: BASF AG (BADI )

Inventor: CAPELLER L; GORLACH R; SCHOLZ D

Number of Countries: 001 Number of Patents: 001

Patent Family:

Patent No	Kind	Date	Applicat No	Kind	Date	Week
DE 3423766	A	19850103	DE 3423766	A	19840628	198502 B

Priority Applications (No Type Date): DE 3323522 A 19830630; DE 3423766 A 19840628

Abstract (Basic): DE 3423766 A

Composite structure comprising (A) foamed layer of predominantly closed cell foamed plastic and (B) a top layer bonded thereto, of granular inorganic additive and organic binder having water vapour diffusion equiv. air layer thickness, as measured according to DIN 52615, less than 1.0 m.

Pref. (A) is 3-12 cm. thick, (B) is 0.3-3.0 cm. thick. (A) pref. comprises extruded polystyrene foam, density 25-60 kg./cub. m. In prepn. of (B), 10-25 pts. vol. binder and 5-20 pts. vol. water are pref. used per 100 pts. bulk vol. filler. Glass fibre lattice fabric is pref. inserted between (A) and (B). Filler pref. comprises 80-100 vol.% dried pumice granulate and/or river sand of average particle size 1.0-3.0 mm. and 0-20 vol.% river sand or pumice sand with average particle size 0.1-1.0 mm.

USE/ADVANTAGE - Heat-insulation of flat roofs by bonding onto water-impermeable roof skin. Structure has good water vapour permeability, reflects solar radiation well, has good resistance to fire spread and heat radiation, and low wt.

0/1

Title Terms: STRUCTURE; HEAT; INSULATE; FLAT; ROOF; COMPRISE; CLOSE; CELL; FOAM; PLASTIC; LAYER; TOP; LAYER; FILLED; ORGANIC; BIND

Derwent Class: A32; P73; Q43; Q45

International Patent Class (Additional): B32B-027/14; E04B-001/78; E04D-003/35

File Segment: CPI; EngPI

Manual Codes (CPI/A-N): A12-R05; A12-R06; A12-S04B

Plasdoc Codes (KS): 0011 0231 0304 0486 0487 3183 3181 1373 1601 2020 2198

2214 2294 2445 2493 2499 2504 2538 2540 2592 2646 2654 2665 2679 3255

3256 3258 2682 2696 2697 2726 3275

Polymer Fragment Codes (PF):

\*001\* 014 034 04- 055 056 074 081 143 146 199 220 221 226 231 273 308 309  
336 341 359 397 400 415 436 441 443 448 472 473 477 491 492 50& 50-  
516 521 539 540 57& 575 58& 581 596 604 606 609 613 616 617 623 626  
651 688 720 723

Derwent Registry Numbers: 5214-U

PUB-NO: DE003423766A1

DOCUMENT-IDENTIFIER: DE 3423766 A1

TITLE: Composite elements for thermal  
insulation of flat roofs

PUBN-DATE: January 3, 1985

INVENTOR-INFORMATION:

NAME	COUNTRY
CAPELLER, LUDWIG DR	DE
GOERLACH, REINHOLD	DE
SCHOLZ, DANKMAR	DE

ASSIGNEE-INFORMATION:

NAME	COUNTRY
BASF AG	DE

APPL-NO: DE03423766

APPL-DATE: June 28, 1984

PRIORITY-DATA: DE03423766A ( June 28, 1984) , DE03323522A  
( June 30, 1983)

INT-CL (IPC): E04D003/35, E04B001/78 , B32B027/14

EUR-CL (EPC): B32B027/14 ; E04D003/35

US-CL-CURRENT: 428/117

ABSTRACT:

CHG DATE=19990617 STATUS=O> Prefabricated composite  
elements for thermal  
insulation of flat roofs comprising a foam layer of a  
predominantly  
closed-celled foam plastic and, bonded thereto, a cover  
layer of a granular

inorganic aggregate and an organic binder. The composite element is characterised by its high water vapour permeability, expressed by a water vapour diffusion equivalent air layer thickness according to DIN 52615 of less than 1.0 m.